

TEKNİK BİLGİ FORMU

BA38B555

Ürün Tanımı

Renk

Ürün Özellikleri

Ambalaj Viskozitesi

Amb.Vis.de Yoğunluk

Amb. Visk.de Katı Madde,Ağırlıkça

Teorik Kaplama Alanı

Uygulama Tavsiyeleri

Uygulama Yöntemi

Uygulama Viskozitesi

Karışım Oranı

Karışım Kullanım Süresi, 20°C

Uygulama Koşulları

Kuruma Koşulları

Uygulama Miktarı

Uygulanacak Yüzey

Yüzey Hazırlığı

Güvenlik ve Depolama Bilgileri

Depolama Süresi

POLİÜRETAN BEYAZ ASTAR 3+1

Alkid reçineleri içeren,iki bileşenli, poliüretan esaslı astardır. Yüksek doldurma ve örtme gücüne sahiptir ve her türlü ahşap yüzeye mükemmel yapışır. Çok iyi yayılma ve zımparalanma özellikleri sayesinde üzerine uygulanacak sonkat boyaların düzgün yüzey vermesini sağlar. İç kullanım amaçlı mobilyaların her türlü MDF, masif ve kaplama ahşap yüzeylerin astarlanmasında kullanılır. Çatlama riskini minimize etmek için MDF kesitleri ve frezeli bölgeler gibi düşük yoğunluklu MDF yüzeylerine astardan önce Bariyer Vernik (BV38Z209) uygulanması önerilir. Bu ürünün ambalaj halindeki teorik VOC değeri 366 g/L'dir.

Beyaz. İstek üzerine yeni renkler yapılabilir.

125-150 sn / DIN CUP 6 / 20°C

1.5-1.6 gr / cm³

% 74-78

1 kg. karışım ile 30-35 µ kuru film bırakacak şekilde tatbik edildiğinde 8-10 m² alan boyanabilir.

Not: Gerçekte kaplama alanı parçanın şekli, yüzey bozukluğu, uygulama yöntem ve uygulama koşulları gibi birçok faktöre bağlı olarak değişiklik gösterir.

Emişli veya hazneli tipte havalı tabanca

15-17 sn / DIN CUP 4 / 20°C

Boya (BA38B555)

: 100 kısım (ağırlıkça)

Sertleştirici (BB38Z555)

: 33 kısım (ağırlıkça)

Tiner (TB0038)

: 15-20 kısım (ağırlıkça)

3 saat

15°C - 30°C, %40-%70 RH

20°C'de, 16 saat (obje sıcaklığı)

300-350 gr/m²

MDF

Uygulama yapılacak yüzey her türlü toz,kir,yağ v.s.'den arındırılmış olmalıdır.

Orijinal ambalajının açılmaması durumunda , 5°C-30°C sıcaklıklar arasında , normal stoklama koşullarında en az 12 ay süreyle

Sistemlerimizin etkinliği,laboratuvar araştırmaları ve yıllar süren pratik tecrübelerimiz üzerine kurulmuştur.Ürünler, talimatlara göre ve iyi bir işçilikle uygulandığında ortaya çıkan işin kalitesinin AkzoNobel Kemipol standartlarına uygun olacağı tarafımızdan garanti edilmektedir. Ancak, elde edilen sonucun kontrolümüz dışında olan faktörlerle etkilenmesi durumunda sorumluluk kabul edilemez. Müşteri, satın aldığı ürünlerin söz konusu uygulamaya uygun olup olmadığını normal olarak sahip olması gereken yöntemlerle kontrol etmek durumundadır.

AkzoNobel Kemipol San.Tic. A.Ş.

Ankara Karayolu 25. Km. 35177 Kemalpaşa - İzmir / Türkiye

Tel:+90.232.8701470 Fax:+90.232.8770070 / 8771114 www.akzonobel.com/kemipol



Sağlık ve Güvenlik

depolanabilir.

Etiket üzerindeki uyarılara bakınız. Taşınması, depolanması ve atıkların yok edilmesi sırasında, ilgili yasa ve tüzüklere uyulmalıdır. Detaylı bilgi için Malzeme Güvenlik Bilgi Formunu kullanınız.

.....
Sistemlerimizin etkinliği, laboratuvar araştırmaları ve yıllar süren pratik tecrübelerimiz üzerine kurulmuştur. Ürünler, talimatlara göre ve iyi bir işçilikle uygulandığında ortaya çıkan işin kalitesinin AkzoNobel Kemipol standartlarına uygun olacağı tarafımızdan garanti edilmektedir. Ancak, elde edilen sonucun kontrolümüz dışında olan faktörlerce etkilenmesi durumunda sorumluluk kabul edilemez. Müşteri, satın aldığı ürünlerin söz konusu uygulamaya uygun olup olmadığını normal olarak sahip olması gereken yöntemlerle kontrol etmek durumundadır.

AkzoNobel Kemipol San.Tic. A.Ş.

Ankara Karayolu 25. Km. 35177 Kemalpaşa - İzmir / Türkiye
Tel: +90.232.8701470 Fax: +90.232.8770070 / 8771114 www.akzonobel.com/kemipol

TECHNICAL DATA SHEET

BA38B555

Product Description

Color

Material Properties

Delivery Viscosity

Density at Delivery Viscosity

Solid Content at Delivery Viscosityby weight

Theoretical Coverage

Application Recommendations

Application Method

Application Viscosity

Mixing Ratio

Pot Life (20°C)

Application Conditions

Drying Conditions

Application Amount

Substrate

Surface Preparation

Safety and Storage Information

Storage Time

Warnings

POLYURETHANE WHITE PRIMER 3+1

Two component polyurethane based primer, containing alkyd resins. It has high filling and hiding power, and its adhesion to all kinds of wood surfaces is perfect. Owing to its very good levelling and sanding properties, it provides smooth surfaces for topcoats. It can be used as a primer on all kinds of MDF, veneered and solid wood surfaces of indoor-use. To minimise the risk of cracking, it is recommended that first Polyurethane Insulator Varnish (BV38Z209) is applied on low-density MDF surfaces such as cross-sections. The VOC of this product as supplied is 366 g/L.

White. Every shade can be produced upon request.

125-150 s / DIN CUP 6 / 20°C

1.5-1.6 gr / cm³

% % 74-78

At a dry film thickness of 30-35 microns ~ 8-10 m²/kg. The practical coverage depends on the factors, such as shape of the construction, roughness of substrate, method and conditions of application.

Conventional spray gun

15-17 s / DIN CUP 4 / 20°C

Base (BA38B555) : 100 part (by weight)
Hardener (BB38Z555) : 33 part (by weight)
Thinner (TB0038) : 15-20 part (by weight)

3 hours

15°C - 30°C, %40-%70 RH

20°C / 16 h (object temperature)

300-350 gr/m²

MDF

The surface must be removed from any dust,grease, dirt etc.

Minimum 12 months in unbroken original package at 5°C-30°C

See label for precautions. The user of this product is required to comply with the national statutory regulations or health, safety during transportation and at work and waste disposal. See MSDS

The effectiveness of our systems is based on many years' practical experience and laboratory research. We guarantee that the quality of the work performed in accordance with our systems meets the AkzoNobel Kemipol standarts, provided that our instructions are followed carefully and the work is performed in accordance with the requirements as to good craftsmanship. We decline any responsibility, if the final result is affected by factors beyond our control. The customer has to determine the suitability of the delivered products for the intended application by using the means which normally are at his/her disposal.

AkzoNobel Kemipol San.Tic. A.Ş.

Ankara Karayolu 25. Km. 35177 Kemalpaşa - İzmir / Türkiye

Tel:+90.232.8701470 Fax:+90.232.8770070 / 8771114 www.akzonobel.com/kemipol



for detailed information.

.....
The effectiveness of our systems is based on many years' practical experience and laboratory research. We guarantee that the quality of the work performed in accordance with our systems meets the AkzoNobel Kemipol standarts, provided that our instructions are followed carefully and the work is performed in accordance with the requirements as to good craftsmanship. We decline any responsibility, if the final result is affected by factors beyond our control. The customer has to determine the suitability of the delivered products for the intended application by using the means which normally are at his/her disposal.

AkzoNobel Kemipol San.Tic. A.Ş.

Ankara Karayolu 25. Km. 35177 Kemalpaşa - İzmir / Türkiye
Tel:+90.232.8701470 Fax:+90.232.8770070 / 8771114 www.akzonobel.com/kemipol